



TECHNICAL DATA SHEET - PLOTTER VINYLs - SMARTAC EVOLUTION A5000 Series

A 60- μ m, PVC-free, high-performance film, which is coated with a pressure-sensitive, solvent-based, acrylic adhesive. Glossy surface finish.

FILM FEATURES:

	<u>Indicative value</u>	
• Thickness (μ m):	60	
	<u>Average values</u>	<u>Standard</u>
• Tensile Strength (N/25 mm):	min. 15	HEXNFX41021
• Elongation at break (%):	min. 90	HEXNFX41021
• Shrinkage 168 hours at 70 °C (158 °F) (mm):	< 0.8	HEXRET001

LINER:

- Silicone-coated Kraft paper 137 g/m², with grey "THE CAST by HEXIS" print.
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

	<u>Average values</u>	<u>Standard</u>
• Peel strength test 180° on glass (N/25 mm):		HEXFMTM001
after 20 minutes of application	11	
after 24 hours of application	12	
• Initial tack (N/25 mm):	13	HEXFMTM009
• Release (N/25 mm):	0.2	HEXFMTM003

ADHESIVE:

- Solvent-based acrylic adhesive.
- Immediate and permanent adhesion, suitable for wet application to flat surfaces solely.

USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +7 °C (50 °F).
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F).
- Possibility of transferring the film using the HEX905, HEX910, HEX915 or HEX955 tapes.

In order to maintain a uniform appearance of the film and therefore avoid demarcations (whitening), it is recommended to not stretch it beyond 20 % of elongation. The glossy metallised films being more sensitive to elongation must only be applied to flat or 2D surfaces without stretching them.

- In the case of already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

OPERATING RECOMMENDATIONS:

- The colour of the films is monitored by HEXIS to ensure a faithful reproduction of their tints. Nevertheless, should your project require the use of several rolls of the same colour reference, HEXIS recommend using a single batch number of this reference.
- For more information on the application method of SMARTAC EVOLUTION films, please refer to the "Application Guide" on the "Professionals" pages, on our website www.hexis-graphics.com.

STORAGE:

- Shelf life (before application):

The shelf life of this film is 2 years when stored unopened in its original packaging at a temperature ranging from +15 °C to +25 °C (+59 °F to +77 °F) with relative humidity between 30 % and 70 %.

DURABILITY: (Central European climate)

- Vertical outdoor exposure: Up to 8 years.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the media for each application.

The measuring methods for the standards quoted above served as basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use.

All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.