



## CANDYFENCE CF000

### PRODUCT DESCRIPTION:

The PPF range is composed of multi-layered, coloured, self-healing adhesive films, specially designed for decorating and protecting a car's bodywork. Their excellent shock-absorbing properties protect your bodywork against chips caused by stones, insects, car doors, washing brushes, etc. Improved surface sliding. They have a glossy surface finish.

### FILM FEATURES:

Total thickness (film + adhesive)	(Indicative value) <b>195 µm (7.6 mil) ± 10 %</b>	
Tensile strength	(Average values) <b>&gt; 100 N/25 mm</b>	Method <b>HEXNFX41021</b>
Elongation at break	(Average values) <b>&gt; 350 %</b>	Method <b>HEXNFX41021</b>
Shrinkage 168 hours at 70 °C (158 °F)	(Average values) <b>&lt; 0.2 mm</b>	Method <b>HEXRET001</b>

### LINER:

50-µm PET film (exclusively for CF001).

150-µm, silicone-coated, embossed PET liner.

### ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

Peel strength test at 180°

after 20 minutes of application	(Average values) <b>14 N/25 mm</b>	Method <b>HEXFTM001</b>
after 24 hours of application	(Average values) <b>17 N/25 mm</b>	Method <b>HEXFTM001</b>
Initial tack	(Average values) <b>19 N/25 mm</b>	Method <b>HEXFTM009</b>
Release	(Average values) <b>0.3 N/25 mm</b>	Method <b>HEXFTM003</b>

### ADHESIVE:

Solvent-based acrylic adhesive.

Immediate and permanent adhesion, optimal after 24 hours of contact.

### USER'S INSTRUCTIONS:

Dry application method

*It is mandatory to use the nominal «dry» application method with the CF001 film, due to its embossed liner. This technology allows easy repositioning of the film on the substrate during application, while not excluding the squeegeeing step for optimal adhesion of the film to the substrate.*

Recommended minimum application temperature: +10 °C (+50 °F) Apply preferably between +15 °C and +35 °C (+59 °F and +95 °F).

Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)

- The CANDYFENCE film range is intended for partial or full wrapping of vehicle car bodies and offers at the same time effective protection.
- The surface protection film must be removed before CANDYFENCE is processed (cutting with the plotter or film application).
- The film must be thoroughly inspected after removing the surface protection film and before removing the back side protection liner.

*HEXIS absolve themselves from any liability in the case of complaints made after the report of an appearance flaw (scratches, bubbles, matt area...) noticed during removal of the PET liner.*



- Cut the film to the size of the part to be wrapped, allowing +10 cm (4 in.) of extra margin.

*The remaining film must be stored on its original core (do not cut the rolls into several lengths or widths, do not repackage the product); the roll must be closed immediately and properly protected (masking tape or roll-collars) after use in order to preserve all its qualities.*

- Apply to a surface that is clean and free from any traces of contaminants (dust, grease, wax, silicone, etc.).

*Particular care must be taken to clean the angles and periphery of the target surfaces in order to enable the film to adhere properly to the surface.*

- In the case of painted substrates, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

## OPERATING RECOMMENDATIONS:

- Conformable product developed for the protection of bodywork, underbody, painted plastic bodywork parts (bumpers, rear-view mirror casings, strips, etc.) against chips caused by stones and insects.
- Excellent protection against vandalism (key scratches).
- The improved surface sliding of the films of the CANDYFENCE range enables you to reduce squeegee friction during application and facilitates the film cleaning.
- To facilitate application, HEXIS have several types of squeegees in their range of accessories, ranging from soft to hard (plastic or felt).
- In the case of superficial micro-scratches, the film is able to eliminate these scratch marks when the temperature ranges from 45 °C to 70 °C (from 113 °F to 158 °F) maximum. For this purpose, heat must be applied using a heat gun to activate the self-healing power of the film.
- For more information on the application method of the films of the CANDYFENCE range, please refer to the Application Guide on the «Professionals» pages, category «Solar and safety films» on our site [www.hexis-graphics.com](http://www.hexis-graphics.com).

## STORAGE:



Storage period before use  
**1 year**



Storage temperature  
**+15 °C to +25 °C (+59 °F to +77 °F)**



Relative humidity during storage  
**with relative humidity of 50 %**



Storage area  
**in a dust-free environment**



Storage method before use  
**in its original packaging**



Orientation of rolls before use  
**vertically**

## DURABILITY: CENTRAL EUROPEAN CLIMATE

- Vertical exposure:  
up to 10 years (under normal road use conditions).
- Lifespan depends on the type of substrate, its preparation, exposure conditions and nature and frequency of the cleaning.

*For instance, it is estimated that a south-facing exposure will divide the durability by two. The same applies to a horizontal exposure. In addition, elevated temperatures (above +50 °C) (+122 °F) or pollution significantly reduce this durability.*

*To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site [www.hexis-graphics.com](http://www.hexis-graphics.com).*

## NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. In case of doubt, request an expert evaluation of the compatibility of the film and the glass in question. All of the published information is based on measurements regularly performed in the laboratory. The published information does not, however, constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website [www.hexis-graphics.com](http://www.hexis-graphics.com).