


HX203EG



PRODUCT DESCRIPTION:

Printable film composed of a 80- μ m, calendered, polymeric PVC, which is coated with a pressure-sensitive, acrylic adhesive. Intended for solvent, eco-solvent, latex and UV inkjet printing. Etched glass surface finish.

FILM FEATURES:

• Thickness	(Indicative value) 80 μm	
• Total thickness	(Indicative value) 275 μm	
• Total weight	(Average values) 280 g/m²	Method HEXGSM001
• Tensile strength	(Average values) min. 35 N/25 mm	Method HEXNFX41021
• Elongation at break	(Average values) min. 100 %	Method HEXNFX41021
• Shrinkage 168 hours at 70 °C (158 °F)	(Average values) < 0.4 mm	Method HEXRET001

LINER:

- Silicone-coated and embossed PE paper 145 g/m² with light grey HEXIS print.
- Stable under hygrometric variations

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

• Peel strength test at 180°; Measurement support glass	(Average values)	Method
after 20 minutes of application	21 N/25 mm	HEXFTM001
after 24 hours of application	(Average values) 23 N/25 mm	Method HEXFTM001
• Initial tack	(Average values) 21 N/25 mm	Method HEXFTM009
• Release	(Average values) 0.3 N/25 mm	Method HEXFTM003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

ADHESIVE:

- Solvent-based acrylic adhesive.
- Structured adhesive for faster application and air evacuation.
- Immediate and permanent adhesion, optimal after 24 hours of contact.


PRINTING GUIDE:

- Touch-dry after less than 15 minutes depending on printer used.
- Optimal drying time for the inks before laminating, coating or further processing is 24 hours.

USER'S INSTRUCTIONS:

- Dry application method

It is mandatory to use the so-called «dry» application method with this film, due to its HEX'PRESS liner. This technology means you can easily reposition the film on the substrate during application, while not excluding the squeegeeing step for optimal adhesion of the film to the substrate.



USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +10 °C (+50 °F)
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)
- Hygrometry influences the quality of the application.

On a cold window condensation may occur between the window and the adhesive film; it is therefore advisable to heat the substrate.

- Adhesion to glass, steel, aluminium, PVC, melamine, etc. except grain substrates or substrates coated with acrylic paint.
- In the case of an already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

OPERATING RECOMMENDATIONS:

- Optimal drying time for the inks before laminating or further processing is 24 hours minimum.
- The surface finish of your printings may be modified/improved/protected by applying the appropriate laminate: V750 or PC500. For UV printings, use the protective VCR750 laminate.

Caution: *Applying a laminate can strongly reduce the etched glass surface finish of the HX203EG film.*

- The colour of the films is controlled by HEXIS in order to ensure faithful reproduction of their colour tints. Nevertheless, in the case that your project requires the use of several rolls of the same colour reference, HEXIS recommend using only a single batch number of each reference

STORAGE:



Storage period before use
1 year



Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage
with relative humidity of 50 %



Storage area
in a dust-free environment



Storage method before use
in its original packaging



Orientation of rolls before use
vertically

DURABILITY: (Central European climate)

- Vertical outdoor exposure:
 - Unprinted: 5 years.
 - Printed and laminated:
 - PC500: 5 years,
 - V750: 4 years,
 - VCR750: 3 years.
 - Printed: 2 years.

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site www.hexis-graphics.com.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.