

### **TECHNICAL DATA SHEET**





# **HXS5CANB**



#### PRODUCT DESCRIPTION:

Film composed of an 140-µm, calendered, polymeric PVC, which is coated with a pressure-sensitive, acrylic adhesive. Structured adhesive for faster application and air evacuation. Decorative film with «carbon fibre» effect, for use on flat surfaces.

### **FILM FEATURES:**

| · Thickness                             | (Indicative value)<br><b>140 µm</b> |                              |
|---|-------------------------------------|------------------------------|
| · Tensile strength                      | (Average values) min. 35 N/25 mm    | Method<br><b>HEXNFX41021</b> |
| · Elongation at break                   | (Average values) min. 50 %          | Method<br><b>HEXNFX41021</b> |
| · Shrinkage 168 hours at 70 °C (158 °F) | (Average values) < 0.5 mm           | Method<br><b>HEXRET001</b>   |

#### LINER:

- · Silicone-coated and embossed PE paper 145 g/m² with light grey HEXIS print.
- · Stable under hygrometric variations

#### **ADHESIVE PROPERTIES:**

(Measured average values at publication of the technical data sheet)

· Peel strength test at 180°; Measurement support glass

|                                 | (Average values)                    | Method                     |
|---------------------------------|-------------------------------------|----------------------------|
| after 20 minutes of application | 14 N/25 mm                          | HEXFTM001                  |
|                                 | (Average values)                    | Method                     |
| after 24 hours of application   | 16 N/25 mm                          | HEXFTM001                  |
|                                 | (Average values)                    | Method                     |
| · Initial tack                  | 17 N/25 mm                          | HEXFTM003                  |
| · Release                       | (Average values) <b>0.2 N/25 mm</b> | Method<br><b>HEXFTM003</b> |
|                                 | -                                   |                            |

 Resistance to solvents: the adhesive is resistant to most chemicals (alcohol, petrol, diluted acids, oils, fuels).

#### ADHESIVE:

- · Solvent-based acrylic adhesive.
- · Structured adhesive for faster application and air evacuation.
- · Immediate and permanent adhesion, optimal after 24 hours of contact.

#### **USER'S INSTRUCTIONS:**

· Dry application method

It is mandatory to use the so-called «dry» application method with this film, due to its HEX'PRESS liner. This technology means you can easily reposition the film on the substrate during application, while not excluding the squeegeeing step for optimal adhesion of the film to the substrate.

- · Recommended minimum application temperature: +10 °C (+50 °F)
- · Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)
- Sens d'application du film: For a uniform visual aspect, it is necessary to keep the same film application direction in order to ensure colour homogeneity according to the viewing angle.
  - · Film with «carbon fibre» surface finish, for the decoration of flat surfaces.
  - The HXS5CANB carbon effect film is a fragile product, which is sensitive to scratching and pressure marks. To be handled with care.
  - Possibility of transferring the HXS5CANB film using the tapes HEX910, HEX915 or HEX930.



## **TECHNICAL DATA SHEET**





- · Adhesion to glass, steel, aluminium, PVC, melamine, etc. except grain substrates or substrates coated with acrylic paint.
- In the case of an already painted substrate, self-adhesive media must only be applied to undamaged original paintwork.
   If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

#### STORAGE:



Storage period before use **2 years** 



Storage temperature

+15 °C to +25 °C (+59 °F to +77 °F)

**DURABILITY:** (Central European climate)

· Vertical exposure on flat surfaces:

Outdoor: 5 years. Indoors: 10 years.



Relative humidity during storage with relative humidity between 30 % and 70 %



Storage method before use in its unopened original packaging

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site www.hexis-graphics.com.

#### NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.