



POD220SOLV



PRODUCT DESCRIPTION:

230-µm white translucent polyester film. For solvent, eco-solvent, latex and UV inkjet printing. For application to lightboxes. High-gloss surface finish.

FILM FEATURES:

- Total thickness (Indicative value)
230 µm
- Total weight (Indicative value)
295 g/m²

PRINTING GUIDE:

- The printable side is the glossy one (outer side).
- For latex printing, always carry out a preliminary test to define optimal adjustment of printing parameters and ink drying temperatures in order to avoid any risk of material deformation.
- Printing temperature range: +15 °C to +30 °C (+59 °F to +86 °F) with relative humidity between 30 % and 60 %.
- Touch-dry after less than 10 minutes depending on printer used.
- Optimal drying time for the inks before laminating, coating or further processing is 24 hours.
 - The surface finish of your printings may be modified/improved/protected by laminating them with the appropriate V700 (matt, satin or glossy) or GFLI130 laminate. DO NOT USE heat-sealing (heat encapsulating) film.
- Pour les impressions Latex toujours réaliser un test préalable d'ajustement optimal des paramètres d'impression et températures de séchage des encres afin de prévenir tous risques de déformation du support.

STORAGE:



Storage period before use
1 year



Relative humidity during storage
with relative humidity between 35 % and 65 %



Storage temperature
+10 °C to +30 °C (+50 °F to +86 °F)



Storage method before use
in its unopened original packaging

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the absolute suitability of the medium for each specific application. All of the published information is based on measurements regularly performed in the laboratory. All the published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.