



POP200ECOS



PRODUCT DESCRIPTION:

205-µm, white/grey, opaque polypropylene film. For solvent, eco-solvent, latex and UV inkjet printing. Satin surface finish.

FILM FEATURES:

- Total thickness (Indicative value)
205 µm
- Total weight (Indicative value)
170 g/m²

PRINTING GUIDE:

- For latex printing, always carry out a preliminary test to define optimal adjustment of printing parameters and ink drying temperatures in order to avoid any risk of material deformation.
- Printing temperature range: +15 °C to +30 °C (+59 °F to +86 °F) with relative humidity between 30 % and 60 %.
- Touch-dry after less than 10 minutes depending on printer used.
- Optimal drying time for the inks before laminating, coating or further processing is 24 hours.

USER'S INSTRUCTIONS:

- Suitable for roll-up and wall displays.

Anti-curling film: prevents self-curling. Scratch-resistant film: protective lamination not necessary.

- The surface finish of your printing may be modified/improved by the judicious choice of one of the laminating films V650, V700, V750 or GFL1130. **DO NOT USE** heat-sealing (heat encapsulating) film.

During lamination, make sure that the tension between the protection film and the visual is the same in order to avoid any unwanted curling effect.

STORAGE:



Storage period before use
1 year



Storage temperature
+10 °C to +30 °C (+50 °F to +86 °F)



Relative humidity during storage
with relative humidity between 30 % and 65 %



Storage method before use
in its unopened original packaging

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the absolute suitability of the medium for each specific application. All of the published information is based on measurements regularly performed in the laboratory. All the published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.