

TECHNICAL DATA SHEET















PRODUCT DESCRIPTION:

85-µm, adhesive-coated polyurethane film, made from a water-based emulsion, which is free of DMF or similar solvents. Opaque white, thin film, recommended for applications to cotton and polyester textiles (except Softshell). Especially adapted for the creation of letterings, logos or small images. Matt surface finish.

FILM FEATURES:

· Thickness

(Indicative value)

85 µm

LINER:

· 105-µm polyester backing paper.

APPLICATION GUIDE FOR FLEX:

- Good adhesion to cotton and polyester.
- Do not use the UFLEX7PV2 film on Softshell fabrics.

For any other type of textile, carry out a test to check the resistance of the fabric to the press temperature and the compatibility of the UFLEX7PV2 film with the cloth.

Print the image in positive mode.

Cutting and weeding



- · Cut and weed the image.
- Minimum cutting size (unprinted areas or perfectly dry, printed areas): 0,6 cm (0.24 in.) (height of letters).



Prerequisites

It is preferable to apply the film to previously washed fabrics.

Preheat press and textile prior to application.



Pressing temperature

140 °C (284 °F)



Pressing duration

15 secondes

In any case, always perform a preliminary trial so as to best adjust the pressing conditions before carrying out large series.



Pressing strength

high pressure

Carefully remove the transfer tape while the film is still:



Protector removal

not

Place parchment paper on the graphic's surface.



Repressing temperature 140 °C (284 °F)



Repressing duration

5 secondes

After pressing, wait for at least 24 hours before washing the garment. For better ink durability, it is preferable to wait for one week before carrying out the first washing.



Washing temperature

with a maximum of 60 °C (140 °F)



Washing conditions

Use laundry products without chlorine bleach.



Drying conditions

Tumble drying is prohibited.



Ironing conditions

Iron your garment inside out.

OPERATING RECOMMENDATIONS:

• For each new application of UFLEX7PV2 films to Lycra® based fabrics, verify the compatibility of the UFLEX7PV2 film with this material by producing a garment corresponding to the end product.

Due to the high variability of these substrates, HEXIS decline all responsibility related to the behaviour of the end product.

- · The use of softeners is not recommended since it can cause an alteration of the flex film adhesion to the fabric.
- For more information on the application method of the UFLEX7PV2 film, please refer to the PRINTFLEX Application Guide available under the "Professionals" heading, in the "Films for textile" category on our website www.hexis-graphics.com.



TECHNICAL DATA SHEET





STORAGE:



Storage period before use





Storage temperature

+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage with relative humidity between 30 % and 70 %



Storage method before use in its unopened original packaging

CERTIFICATION:

OEKO-TEX certification



STANDARD 100

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.