



TECHNICAL DATA SHEET - PLOTTER VINYLS **STENCIL**

Stencil film composed of a 80-µm, calendered, semi-polymeric PVC, which is coated with a removable, pressure-sensitive, acrylic adhesive.

FILM FEATURES:

| | ٠ . | | - 1 | |
|------|-------|--------|-----|------|
| Ind | licat | בועם | Va | בווו |
| 1110 | ncat | .1 4 C | v a | uc |

• Thickness (µm): 80

| Thickness (pm). | 00 | |
|---|--|---|
| | Average values | <u>Standard</u> |
| Tensile Strength (N/25 mm): | min. 35 | HEXNFX41021 |
| Elongation at break (%): | min. IIO | HEXNFX41021 |
| Shrinkage 168 hours at 70 °C (158 °F) (mm): | < 0.2 | HEXRET001 |
| | Tensile Strength (N/25 mm): Elongation at break (%): Shrinkage 168 hours at 70 °C (158 °F) (mm): | Tensile Strength (N/25 mm): min. 35 Elongation at break (%): min. 110 |

LINER:

- Silicone-coated Kraft paper 137 g/m², with grey HEXIS print.
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

| | | Average values | <u>Standard</u> |
|---|---|----------------|-----------------|
| • | Peel strength test 180° on glass (N/25 mi | m): | HEXFTM001 |
| | after 20 minutes of application | 2 | |
| | after 24 hours of application | 3 | |
| • | Initial tack (N/25 mm): | 3 | HEXFTM009 |
| • | Release (N/25 mm): | 0.1 | HEXFTM003 |

• Resistance to solvents: the adhesive is resistant to most chemicals (alcohol, petrol, diluted acids, oils, fuels).

ADHESIVE:

- Solvent-based acrylic adhesive.
- Immediate adhesion; removable adhesive.

USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +10 °C (+50 °F).
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F).
- In the case of already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

STORAGE:

• Shelf life (before application):

The shelf life of this film is 2 years when stored unopened in its original packaging at a temperature ranging from +15 °C to +25 °C (+59 °F to +77 °F) with relative humidity between 30 % and 70 %.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the media for each application.

The measuring methods for the standards quoted above served as basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use.

All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.