



TECHNICAL DATA SHEET - PROTECTIVE FILM BSE100iV2

100- μ m safety film. UV-proof. Anti-scratch coating. Indoor application.

This film for glazing allows to increase the time to break the glass in the case of intrusion by burglary. The film retains the glass splinters caused by accidental glass breakage or vandalism and thus prevents injuries and wounds.

Colour: Clear.

FEATURES OF THE UNPRINTED FILM:

Indicative values

(values for a film applied to a 3-mm clear glazing)

- | | |
|--|-----|
| • Thickness (μ m): | 100 |
| • Solar transmission (%): | 83 |
| • Solar reflection (%): | 9 |
| • Solar absorption (%): | 8 |
| • Solar energy rejection (%): | 16 |
| • Visible light transmission (%): | 90 |
| • Visible light reflection (ext.) (%): | 7 |
| • Visible light reflection (int.) (%): | 4 |
| • UV transmission (%): | 5 |

FILM COMPATIBILITY: (vertical application, unprinted film)

Type of glazing		Compatibility
Simple glazing	Clear	Yes
	Tinted	Yes
	Tinted, mirrored	Yes
Double glazing	Clear	Yes
	Tinted	Yes
	Tinted, mirrored	Yes
	Low emission (inert gas fill)	Yes
	Laminated, clear (laminated glass facing outwards of the building)	Yes
	Laminated, clear (laminated glass facing inwards of the building)	Yes

USER'S INSTRUCTIONS:

- Prior to any film application to a substrate prone to degassing, it is the responsibility of the prescriber and applicator to make sure of the compatibility between the film and the substrate and carry out an optimal substrate degassing (in the case of synthetic glass such as PMMA, polycarbonate, etc.). The applicator is liable for any appearance of bubbles due to substrate degassing.
- Indoor application.
- Application to vertical glass surfaces, up to a maximum of 2.5 m².
- During storage, always handle with clean and dry hands.
- Always remove the liner at the moment right before application, and squeegee the film right after as instructed during the HEXIS training courses.
- Application with soapy water only.
- Adhesion to glass, except grain substrates.
- Only use special tools dedicated to the application of solar / safety films.
- The film should not be covered by stickers or self-adhesive films.
- If peeled off after its application, the deterioration of the structure and appearance of the film will be irreversible.
- After application you must wait for one month before cleaning the film's surface with soapy water for the first time.

OPERATING RECOMMENDATIONS:

- For further information on the application method, please refer to the Application Guide available under the "Professionals" headings, category "Solar and safety films" on our website www.hexis-graphics.com.

STORAGE:

- Shelf life (before use):

The shelf life of this film is 3 years when stored horizontally in a dust-free environment at a temperature ranging from 15 °C to 25 °C (+59 °F to +77 °F) with relative humidity of 50 %.

DURABILITY:

- Vertical exposure: 12 years.

NOTES:

The compatibilities indicated in the table "Film Compatibility" are provided for information purposes only for a unprocessed film and must be confirmed on a case-by-case basis. Due to the great variety of glazing and exposure possibilities, it is the responsibility of the customer/the person in charge of application to carry out a detailed compatibility study between the glass/film and the use-related impacts. These evaluations should be accomplished prior to product implementation in order to determine if it is suitable or not for the intended purpose. HEXIS are not liable for glass breakage by thermal shock caused by incompatibility between the glazing and the processed film or by window film application to a defective glazing. All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.