


**TECHNICAL DATA SHEET - DIGITAL PRINTING - ANTI-GRAFFITI - PERMANENT ADHESIVE**
**AGCR 700**

Film composed of a 36- $\mu$ m polyester, which is coated with a pressure-sensitive acrylic adhesive. Glossy surface finish for cold laminating. Particularly suitable for laminating UV inkjet printing.

**FILM FEATURES:**

	<u>Average values</u>	<u>Standard</u>
• Thickness ( $\mu$ m):	36	
• Tensile strength (N/25 mm):	> 100	HEXNFX41021
• Shrinkage 168 hours at +70 °C (+158 °F) (mm):	< 0.2	HEXRET001
• Surface roughness ( $\mu$ m):	< 5*	HEXRUG001

\* A surface roughness of less than 10  $\mu$ m indicates a floor that can be potentially hazardous in wet conditions. Do not apply to floors.

**LINER:**

- Silicone-coated paper 80 g/m<sup>2</sup>, with grey HEXIS print.
- Stable under hygrometric variations.

**ADHESIVE PROPERTIES:**

(Measured average values at publication of the technical data sheet)

	<u>Average values</u>	<u>Standard</u>
• Peel strength test 180° on glass (N/25 mm):		HEXFTM001
after 20 minutes of application	14	
after 24 hours of application	16	
• Initial tack (N/25 mm):	23	HEXFTM009
• Release (N/25 mm):	0.1	HEXFTM003
• Resistance to solvents: the adhesive is resistant to most chemicals (alcohol, diluted acids, oils, ketones).		

**ADHESIVE:**

- Solvent-based acrylic (adhesive non-repositionable).
- Immediate and permanent adhesion.

## **USER'S INSTRUCTIONS:**

- Recommended minimum application temperature: +10 °C
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)
- The film can be cleaned with a non-abrasive sponge or a soft cloth and acetone, alcohol, soapy water or HEX'AG.
- Particularly suitable for cold laminating UV inkjet prints,

*Although the ink is solid immediately after printing, the polymerisation and reticulation time of the inks is 24 hours (variable upon the printer used and the quantity of ink applied). Please comply with this minimum waiting time before laminating the UV inkjet printed film.*

- In the case of already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

## **STORAGE:**

- Shelf life (before use):

The shelf life of this film is 2 years when stored upright in its original packaging in a dustfree environment at a temperature ranging from +15 °C and +25 °C (+59 °F to +77 °F) with relative humidity of 50 %.

## **DURABILITY:** (Central European climate)

- Vertical outdoor exposure:  
Film only, without graffiti, not cleaned using solvents: 3 years.  
Cleaned film: dependent on the method and frequency of the cleaning.
- The durability of the laminated printing depends on the printing technology used and the inks used. Consult the ink manufacturer.

## **NOTES:**

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the media for each application.

The measuring methods for the standards quoted above served as basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use.

All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website [www.hexis-graphics.com](http://www.hexis-graphics.com).