



## TECHNICAL DATA SHEET - DIGITAL PRINTING - BANNER FRONTOPAC

PVC-coated polyester banner of 680 g/m<sup>2</sup>, suitable for standard solvent, eco-solvent, latex and UV inkjet printing. Satin surface finish, inkjet varnish on both sides for double-sided printing.

### **FEATURES:**

	<u>Indicative values</u>	
• Total thickness of the product (µm):	490	
• Total weight of the product (g/m <sup>2</sup> ):	680	
	<u>Average values</u>	<u>Standard</u>
• Yarn/weft thread (DTEX):	550 x 550	DIN EN ISO 2286-2
• Yarn/weft tear resistance (N):	200/200	DIN53363
• Opacity (%):	100	

### **GENERAL PRINTER COMPATIBILITIES:**

	Solvent	Eco-solvent	Latex	UV
<b>FRONTOPAC</b>	✓	✓	✓	✓

### **USER'S INSTRUCTIONS:**

- Printable on both sides.
- Touch dry after less than 5 minutes depending on printer used.
- Optimal drying time for the inks before laminating or further processing is 24 hours minimum.
- Temperature resistance of the banner: -30 °C to +70 °C (-22 °F to +158 °F).
- Anti-curl properties prevent the banner from curling up over time.
- Banner assembly is possible by using Neoprene<sup>®</sup> glue (I) or double-sided adhesive tape such as STRONGBAN3.

### **STORAGE:**

- Shelf life (before use):  
The shelf life of this film is one year when stored upright in its original packaging in a dust-free environment at a temperature ranging from 15 °C to 25 °C (+59 °F to +77 °F) with relative humidity of 50 %.

### **NOTES:**

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website [www.hexis-graphics.com](http://www.hexis-graphics.com).

(I) Neoprene<sup>®</sup> is a registered trademark of the E.I. du Pont de Nemours and Company.