



TECHNICAL DATA SHEET - DIGITAL PRINTING - POLYESTER - OPAQUE POP 190 ECOS

Film composed of a 180- μm white/grey opaque colaminated polyester. For solvent, eco-solvent, latex and UV inkjet printing. For application on POP DISPLAYS. Satin surface finish.

FILM FEATURES:

Indicative values

- Total thickness of the product (μm): 180
- Total weight of the product (g/m^2): 240
- Opacity (%): > 99

GENERAL PRINTER COMPATIBILITIES:

	Solvent	Eco-solvent	Latex	UV
POP190ECOS	✓	✓	✓	✓

USER'S INSTRUCTIONS:

- Touch-dry after less than 10 minutes depending on printer used.
- The surface finish of your printing may be modified/improved/protected by a judicious choice of laminating films V700 (Matt, Satin or Glossy), PSPOP or GFLI130. DO NOT USE heat-sealing (heat encapsulating) film.
- For any lamination, coating or other, optimal drying time for the inks is 24 hours.
- Operating temperature range: +10 °C to +30 °C (+50 °F to +86 °F) with 30-65 % humidity.
- Substrate/Printing sensitive to water splashing as well as fingerprints (gloves strongly recommended).

STORAGE:

- Shelf life (before application):

The shelf life of this film is 1 year when stored upright and unopened in its original packaging at a temperature ranging from +10 °C to +30 °C (+50 °F to +86 °F) with relative humidity between 30 % and 65 %.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the media for each application. All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.