



## DATA SHEET DIGITAL PRINTING VINYL REMOVABLE ADHESIVE V36IWGI

Monomeric calendered cadmium-free PVC film with a thickness of 80µm, coated with a removable pressure sensitive acrylic adhesive. Destined for inkjet printing with solvent, eco-solvent, HP Latex, UV inks. Gloss finish.

### **CHARACTERISTICS OF THE FILM:**

	<u>Average values</u>	<u>Standard</u>
• Thickness (µm):	80	
• Total caliper (µm):	265	
• Total specific weight (g/m <sup>2</sup> ):	280	HEXGSM00I
• Tensile strength (N/25mm):	min. 60	HEXNFX4I02I
• Elongation at break (%):	min. 150	HEXNFX4I02I
• Dimensional stability (mm): after 168h at 70°C	< 0.4	HEXRET00I

### **GENERAL PRINTER COMPATIBILITIES:**

	<b>Solvent</b>	<b>Eco-solvent</b>	<b>HP-Latex</b>	<b>UV</b>
<b>V36IWGI</b>	✓	✓	✓	✓

### **LINER:**

- Siliconed PE paper 145 g/m<sup>2</sup>, with light blue HEXIS imprint.
- Stable under hygrometric variations.

### **ADHESIVE PROPERTIES:**

(Average values measured at the time of editing the data sheet)

	<u>Average values</u>	<u>Standard</u>
• Peel on glass at 180° (N/25mm): 20 minutes after application	8	HEXFTM00I
24 hours after application	9	
• Initial tack (N/25mm):	7	HEXFTM009
• Release (N/25mm):	0.20	HEXFTM003
• Resistance to solvents: The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

**ADHESIVE:**

- Removable solvent-based acrylic adhesive.
- Immediate adhesion, removable.

**USAGE GUIDE:**

- Touch dry after less than 10 minutes depending on printer used.
- Recommended minimum application temperature: +10°C (+50°F).
- Exposure temperature range (outdoor): -20°C to +60°C (-4°F to +140°F).
- Very good adhesion on glass, steel, aluminium, PVC, melamine,... except grained surfaces or acrylic paints.
- If applied on monomeric or polymeric plasticised vinyl films a removable adhesive may become semi-permanent. The duration of the application and the type of exposure may accelerate the phenomenon.
- In the case of painted substrates self-adhesive media must only be applied onto the undamaged original paintwork. If the paint is not the original paintwork and/or if it is damaged, the application and the removal are at the installer's risk.

**RECOMMENDATIONS FOR USE:**

- Optimum drying time before laminating or further processing is 24 hours minimum.
- The surface aspect can be advantageously modified/improved/protected by applying the appropriate matt, satin or gloss laminate type V700.
- To prevent mechanical and/or chemical aggressions (cleaning) it is recommended to laminate after printing.

**STORAGE:**

- Shelf life (before application):  
1 year if stored at a temperature between +15°C and +25°C (+59°F to +77°F) and 50% relative humidity in the original packing in a vertical position in a dustfree environment.

**DURABILITY:** (Central Europe on flat surfaces)

- Unprinted vertical outdoor exposure: 6 months without notable adhesive residues.
- Printed and laminated vertical outdoor exposure: 12 months (if edges are sealed by a sealing varnish).
- Printed vertical outdoor exposure: 3 months without notable adhesive residues.

**Note:**

Because of the great variety of substrates and possible application methods the installer must examine the suitability of the media for each application. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force. All published data are based on measurements carried out regularly under laboratory conditions. They do, however, not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The seller assumes no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: [www.hexis-graphics.com](http://www.hexis-graphics.com).