



TECHNICAL DATA SHEET - DIGITAL PRINTING - PVC - REMOVABLE ADHESIVE V362CGI

Film composed of an 80- μ m calendered, monomeric PVC, which is coated with a removable pressure-sensitive acrylic adhesive. For solvent, eco-solvent, latex and UV inkjet printing. Glossy clear surface finish.

FILM FEATURES:

	<u>Indicative values</u>	
• Thickness (μ m):	80	
• Total thickness of the product (μ m):	270	
	<u>Average values</u>	<u>Standard</u>
• Total weight of the product (g/m^2):	290	HEXGSM001
• Tensile strength (N/25 mm):	min. 40	HEXNFX4102I
• Elongation at break (%):	min. 100	HEXNFX4102I
• Shrinkage 168 hours at 70 °C (158 °F) (mm):	< 0.8	HEXRET001

GENERAL PRINTER COMPATIBILITES:

	Solvent	Eco-solvent	Latex	UV
V362CGI	✓	✓	✓	✓

LINER:

- Silicone-coated PE paper 145 g/m^2 with light blue HEXIS print.
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

	<u>Average values</u>	<u>Standard</u>
• Peel strength test 180° on glass (N/25 mm): after 20 minutes of application	8	HEXFTM001
after 24 hours of application	10	
• Initial tack (N/25 mm):	10	HEXFTM009
• Release (N/25 mm):	0.1	HEXFTM003
• Resistance to solvents: the adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

ADHESIVE:

- Solvent-based acrylic adhesive.
- Immediate adhesion; removable adhesive.

USER'S INSTRUCTIONS:

- Touch-dry after less than 10 minutes depending on printer used.
- Recommended minimum application temperature: +10 °C (+50 °F).
- Operating temperature range (outdoors): from -20 °C to +60 °C (-4 °F to +140 °F).
- Very good adhesion to glass, steel, aluminium, PVC, melamine, etc. except grain substrates or substrates coated with acrylic paint.

When applied to laminated monomeric or polymeric PVC films, the removable adhesives can become semi-permanent. The duration of application and the type of exposure may accelerate the phenomenon.

- In the case of an already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

OPERATING RECOMMENDATIONS:

- For all coatings, optimal drying time for the inks is 24 hours minimum.
- The surface finish of your printing may be modified/improved/protected by a judicious choice of laminating films V700 or V650. For UV printing, protect with the laminating film VCR650.
- To avoid any physical and/or chemical (cleaning) damage, it is advisable to laminate after printing.
- For more information on the application method of V362CGI, please refer to its Application Guide on the "Professionals" pages, category "Digital printing media" on our website www.hexis-graphics.com.

STORAGE:

- Shelf life (before application):

The shelf life of this film is 1 year when stored upright in its original packaging in a dust-free environment at a temperature ranging from +15 °C to +25 °C (+59 °F to +77 °F) with relative humidity of 50 %.

DURABILITY: (Central European climate)

- Vertical outdoor exposure on flat surfaces:
Unprinted: 6 months depending on the substrate, without significant traces of adhesive.
Printed and laminated: 12 months (if the print edges are sealed by a sealing varnish).
Printed: 3 months without significant traces of adhesive.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use. All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.