



BLOCKCUT

PRODUCT DESCRIPTION:

110-µm polyurethane film, suitable for hot transfer applications to sublimated fabrics.

FILM FEATURES:

- Film thickness (Average values) **110 µm**

LINER:

- 100-µm polyester backing paper.

APPLICATION GUIDE FOR FLEX:

- Good adhesion to sublimated fabrics.

Carry out a test to check the resistance of the fabric to the press temperature and the compatibility of the flex film with the cloth.



Cutting and weeding

- **Cut a mirror image.**
- **Weed after cutting.**



Prerequisites

It is preferable to apply the film to previously washed fabrics.

- Preheat press and textile prior to application.



Pressing temperature

160 °C (320 °F)



Pressing duration

20 secondes



Pressing strength

moderate pressure

- **Carefully remove the protector (liner):**



Protector removal

warm



Repressing duration

5 secondes

- After pressing, wait for at least 24 hours before washing the garment.

- Turn your garment inside out for washing.



Washing temperature

with a maximum of 40 °C (104 °F)



Washing conditions

Use laundry products without chlorine bleach.



Ironing conditions

Iron your garment inside out.

- For more information on the application method of BLOCKCUT, please refer to the Application Guide on the «Professionals» pages, on our website www.hexis-graphics.com.

STORAGE:



Storage period before use

1 year



Storage temperature

+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage

with relative humidity between 30 % and 70 %



Storage method before use

in its unopened original packaging

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.