



CLIMATE40

PRODUCT DESCRIPTION:

This polyester film is coated with a pressure-sensitive adhesive and intended for solar protection of building windows. Reduces the risk of thermal shock. Anti-UV and anti-heat protection. Anti-scratch treatment. Indoor application.
 Colour: reflective light gold-coloured.

FILM FEATURES:

(values for a film applied to 3-mm clear glass)

Thickness	(Indicative value) 55 µm
Solar energy rejected (heat) (%) :	(Indicative value) 66
Solar energy reflection (%) :	(Indicative value) 47
Solar energy absorption (%) :	(Indicative value) 25
Solar energy transmission (%) :	(Indicative value) 28
Visible light transmission (%) :	(Indicative value) 47
Visible light reflection (%) :	(Indicative value) 29
UV transmission (%) :	(Indicative value) 1

FILM COMPATIBILITY:

Type of glazing	Compatibility
Compatibility with clear single glazing	✓
Compatibility with tinted single glazing	✓
Compatibility with reflective tinted single glazing	✓
Compatibility with clear double glazing	✓
Compatibility with tinted double glazing	✓
Compatibility with reflective tinted double glazing	✓
Compatibility with low emission double glazing (inert gas fill)	✓
Compatibility with clear laminated double glazing (laminated glass facing the exterior of the building)	✓

USER'S INSTRUCTIONS:

Wet application method

The particular technology of this film allows an indoor application, on large glass panels (refer to compatibility chart below) while reducing risks of thermal shock on the glazing (the reduction of the risk does not apply in the case of overlapping or superposing of films).

- Prior to any film application to a substrate prone to degassing, it is the responsibility of the prescriber and applicator to make sure of the compatibility between the film and the substrate and carry out an optimal substrate degassing (in the case of synthetic glass such as PMMA). The applicator is liable for any appearance of bubbles due to substrate degassing.
- Indoor application.
- Application to vertical glass surfaces, up to a maximum of 2.5 m².
- During storage, always handle with clean and dry hands.
- Always remove the liner at the moment right before application, and squeegee the film right after as instructed during the HEXIS training courses.



- Application with soapy water only.
- Adhesion to glass, except grain substrates.
- Only use special tools dedicated to the application of window films.
- The film should not be covered by stickers or self-adhesive films.
- Protect the film edges with a marine type sealing.
- If peeled off after its application, the deterioration of the structure and appearance of the film will be irreversible.
- After application you must wait for one month before any cleaning of the surface with soapy water.

OPERATING RECOMMENDATIONS:

- For further information on the application method, please refer to its Application Guide available under the «Professionals» heading, in the «Solar and safety films» category on our website www.hexis-graphics.com.

STORAGE:



Storage period before use
3 years



Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage
with relative humidity of 50 %



Storage area
in a dust-free environment



Orientation of rolls before use
horizontally

DURABILITY:

- Vertical exposure: 15 years.

WARRANTY :

- The HEXIS warranty covers the CLIMATE40 film in vertical exposure for a period of 10 years against cracking, yellowing and demetallisation.

CERTIFICATION:

Fire-smoke classification



Fire-smoke classification standard

NF P92-512

Reach compliance

The film complies with REACH. It does not contain any substances referenced in ECHA's list of SVHC (Substances of very high concern).

NOTES:

The compatibilities indicated in this table are provided for informational purposes only and must be confirmed on a case-by-case basis. Due to the great variety of glazing and exposure possibilities, it is the responsibility of the customer/the person in charge of application to carry out a detailed compatibility study between the glass/film and the use-related impacts. These evaluations should be done prior to product implementation in order to determine if it is suitable or not for the intended purpose. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.