

EASY2MOVE



PRODUCT DESCRIPTION:

This film is composed of 120-µm, calendered, monomeric PVC, which is coated with a removable adhesive featuring a dot structure (adhesive dots). This structure allows easy air evacuation during film application. The film is intended for short-term indoor or outdoor use. It is digitally printable with solvent, eco-solvent, latex and UV inkjet printers. It has a matt surface finish.

FILM FEATURES:

- Thickness (Indicative value)
120 ±6 µm
- Total thickness (Indicative value)
250 ±12 µm
- Total weight (Indicative value)
270 ±14 g/m²

LINER:

- Silicone-coated PE paper 120 g/m², blank.
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

- Peel strength test at 180° ; Measurement support glass (Indicative value)
after 24 hours of application **2 ±1 N/25 mm**
- Release (Indicative value)
< 0.2 N/25 mm

ADHESIVE:

- Evenly distributed adhesive dots.
- Immediate adhesion; removable adhesive.

PRINTING GUIDE:

- Touch-dry after less than 10 minutes depending on the printer used.

USER'S INSTRUCTIONS:

- Dry application method

Air inclusions that form between the film and the substrate can escape easily due to the structure of the adhesive dots. However, the film must be applied carefully to ensure optimum adhesion of the product to the substrate.

- Operating temperature range: -20 °C to +60 °C (-4 °F to +140 °F) (outdoors)
- Always handle the film with clean hands.
- Adhesion to clean, smooth and flat surfaces.

For any use of the film on structured and/or curved surfaces, it is the responsibility of the customer to verify the compatibility of the film with the substrate. When applied to laminated monomeric or polymeric PVC films, the removable adhesives can become semi-permanent. The duration and type of exposure may accelerate this phenomenon.

- In the case of painted substrates, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

STORAGE:



Storage period before use
1 year




Storage temperature
+15 °C to +30 °C (+59 °F to +86 °F)



Relative humidity during storage
with relative humidity between 45 % and 65 %



Storage method before use
in its unopened original packaging



NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not, however, constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.