

TECHNICAL DATA SHEET





HX241WG2 - HX241WM2











PRODUCT DESCRIPTION:

Film composed of 70-µm calendered PVC, containing polymeric plasticisers and coated with a pressure-sensitive acrylic adhesive. The adhesive is micro-structured for faster application and air evacuation. For solvent, eco-solvent, latex and UV inkjet printing. Glossy (HX241WG2) or matt (HX241WM2) surface finish.

FILM FEATURES:

· Thickness	(Indicative value) 70 µm	
· Total thickness	(Indicative value) 230 µm	
· Total weight	(Average values) 260 g/m²	Method HEXGSM001
· Tensile strength	(Average values) min. 35 N/25 mm	Method HEXNFX41021
· Elongation at break	(Average values) min. 100 %	Method HEXNFX41021
· Shrinkage 168 hours at 70 °C (158 °F)	(Average values) < 0.5 mm	Method HEXRET001

LINER:

- · Silicone-coated and embossed PE paper 145 g/m² with light grey HEXIS print.
- · Stable under hygrometric variations

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

· Peel strength test at 180°; Measurement support glass

	(Average values)	Method
after 20 minutes of application	17 N/25 mm	HEXFTM001
	(Average values)	Method
after 24 hours of application	18 N/25 mm	HEXFTM001
	(Average values)	Method
· Initial tack	21 N/25 mm	HEXFTM009
· Release	(Average values) 0.2 N/25 mm	Method HEXFTM003

• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).

ADHESIVE:

- · Grey, solvent-based acrylic adhesive.
- $\boldsymbol{\cdot}$ Structured adhesive for faster application and air evacuation.
- · Immediate and permanent adhesion.

PRINTING GUIDE:

- · Touch-dry after less than 10 minutes depending on printer used.
- · Optimal drying time for the inks before laminating or further processing is 24 hours minimum.

USER'S INSTRUCTIONS:

· Dry application method

It is mandatory to use the so-called «dry» application method with this film, due to its HEX'PRESS liner. This technology means you can easily reposition the film on the substrate during application, while not excluding the squeegeeing step for optimal adhesion of the film to the substrate.



TECHNICAL DATA SHEET





USER'S INSTRUCTIONS:

- · Recommended minimum application temperature: +10 °C (+50 °F)
- · Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)
 - Vinyl intended for medium-term visual communication on flat surfaces, suitable for outdoor and indoor applications.
- Very good adhesion to glass, steel, aluminium, PVC, melamine, etc. except grain substrates or substrates coated with acrylic paint.
- In the case of painted substrates, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

OPERATING RECOMMENDATIONS:

The surface finish of the printings may be modified/improved/protected by applying the V740 laminate. For UV printings, use the protective VCR740 laminate.

STORAGE:



Storage period before use

1 year



Storage temperature

+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage

with relative humidity between 30 % and 70 %



Storage method before use

in its unopened original packaging

DURABILITY: (Central European climate)

 $\cdot\;$ Vertical outdoor exposure on flat surfaces:

Unprinted: 5 years.

Printed and laminated:

- V740: 3 years.

- VCR740: up to 2.5 years.

Printed: 2 years.

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site www.hexis-graphics.com.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.