



P130



PRODUCT DESCRIPTION:

A 148-µm paper for solvent, eco-solvent, UV and latex inkjet printing. Satin surface finish.

FILM FEATURES:

| | | |
|-------------------|--|---------------------------|
| • Total thickness | (Average values) 148 µm | Method ISO 534 |
| • Total weight | (Average values) 130 g/m² | Method ISO 536 |
| • Opacity | (Average values) > 89 % | Method ISO 2471 |

PRINTING GUIDE:

- Comply with the conditions of storage temperature and hygometry before printing.
- Use the HEXIS ICC profiles, available on our website www.hexis-graphics.com, to perform high quality work while optimising the ink quantity required for this substrate.
- Touch-dry after less than 5 minutes depending on printer used.
- Optimal drying time for the inks before laminating, coating or further processing is 24 hours.

USER'S INSTRUCTIONS:

Water- and weather-proof paper.

OPERATING RECOMMENDATIONS:

- The surface finish of your printings may be modified/improved/protected by applying the appropriate laminate: V650 or V700 (matt, satin or glossy).

It is recommended to laminate the P130 film for any long-term outdoor exposure or if it is subject to severe climate conditions.

- The latex inks are water-sensitive and need to be protected in case of outdoor exposure.
- In the event of frequent cleaning of the graphics, its edges and corners must be protected with a sealing tape or varnish.

STORAGE:



Storage period before use
1 year



Storage temperature
+10 °C to +30 °C (+50 °F to +86 °F)



Relative humidity during storage
with relative humidity between 30 % and 65 %



Storage method before use
in its unopened original packaging

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.