



POP310ECOS



PRODUCT DESCRIPTION:

Film composed of a 310-µm white/silver opaque colaminated polyester, intended for solvent, eco-solvent and latex inkjet printing. Specially adapted for use on POP Displays.

FILM FEATURES:

• Total thickness	(Average values) 310 µm	
• Total weight	(Average values) 420 g/m²	Method HEXGSM001
• Opacity	(Average values) > 99 %	Method HEXOPA001

PRINTING GUIDE:

- Substrate/Printing sensitive to water splashing and fingerprints (wearing gloves and wiping the surface of the product with a cotton cloth before printing are highly recommended).
- Touch-dry after less than 10 minutes depending on printer used.
- Optimal drying time for the inks before laminating, coating or further processing is 24 hours.

USER'S INSTRUCTIONS:

- Operating temperature range: +10 °C to +30 °C (+50 °F to +86 °F)
- Relative humidity during application: with relative humidity between 30 and 70 %
 - Substrate/Printing susceptible to tearing; handle the edges carefully.
 - The grey rear side may be susceptible to scratching. To be handled with care.

OPERATING RECOMMENDATIONS:

- The surface finish of your printings may be modified/improved/protected by applying the appropriate laminate: V700 (matt, satin or glossy) or PSPPOP.

STORAGE:

- | | |
|---|---|
| Storage period before use
1 year | Storage area
in a dust-free environment |
| Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F) | Storage method before use
in its original packaging |
| Relative humidity during storage
with relative humidity of 50 % | Orientation of rolls before use
vertically |

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the absolute suitability of the medium for each specific application. The measuring methods for the standards quoted above served as basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use. All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.