




PURZON060B - PURZON060M (PURZON060 after 01/02/21)



PRODUCT DESCRIPTION:

Film consisting of a 60-µm, transparent, cast PVC containing antimicrobial agents and coated with a pressure-sensitive acrylic adhesive. This film is intended for the protection of surfaces against these types of stress: physical (scratches, deformations, glass breakage), optical (reduces the effects of light on the substrates, or even the oxidation of the substrates) and chemical (creates a physical barrier on the surface of the item by limiting the contact with liquids). Due to its pressure-sensitive adhesive, this film can be used as a temporary protection and can be removed without damaging the substrate. Glossy (PURZON060B) or matt (PURZON060M) surface finish.

The antimicrobial properties of this treated article that incorporates a biocidal product allow for the protection of surfaces against microbes in areas that require a high level of hygiene (hospitals, agribusinesses and food industries, wet rooms, public places, etc.).

FILM FEATURES:

• Thickness	(Indicative value) 60 µm	
• Tensile strength	(Average values) min. 15 N/25 mm	Method HEXNFX41021
• Elongation at break	(Average values) min. 100 %	Method HEXNFX41021
• Shrinkage 168 hours at 70 °C (158 °F)	(Average values) < 0.8 mm	Method HEXRET001

LINER:

- Silicone-coated PE paper with HEXIS print.
- Stable under hygrometric variations

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

• Peel strength test at 180°; Measurement support glass	(Average values)	Method
after 20 minutes of application	19 N/25 mm	HEXFTM001
after 24 hours of application	(Average values) 22 N/25 mm	Method HEXFTM001
• Initial tack	(Average values) 27 N/25 mm	Method HEXFTM009
• Release	(Average values) 0.4 N/25 mm	Method HEXFTM003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

ADHESIVE:

- Solvent-based acrylic adhesive.
- Immediate and permanent adhesion.

USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +10 °C (+50 °F)
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)
- The film can be cleaned/disinfected by all conventional cleaning methods, using non-abrasive accessories, cleaning products, detergents or products currently used in healthcare environments.

The disinfection levels achieved are compatible with common usage in the most sensitive areas in terms of infectious risks (surgery wards, immunocompromised wards, neonatology, etc.).



- The film is resistant to 20 000 cycles of wet abrasion with a non-abrasive sponge (ISO 11998).
- Only apply the film to areas that will not be in direct contact with unpackaged food.
- Compatible with an application to regular or irregular surfaces.
- It can be used as a cold laminate on cast HEXIS digital printing films, compatible with solvent, eco-solvent, latex or UV inkjet technology.
- In the case of an already painted substrate, apply to undamaged original paintwork only. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

OPERATING RECOMMENDATIONS:

- Before applying this laminate to a HEXIS digital printing film, which has been printed with solvent inks, it is recommended to respect the following optimal drying time for the inks:
 - 48 hours if the printed film is cast,
 - 24 hours if the printed film is calendered.
- For more information on the application method of the PURZON060B - PURZON060M films, please refer to the Application Guide on our website www.hexis-graphics.com/en/supports/application-guides.

STORAGE:



Storage period before use
1 year



Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage
with relative humidity of 50 %



Storage area
in a dust-free environment



Storage method before use
in its original packaging



Orientation of rolls before use
vertically

DURABILITY: (Central European climate)

- The bacteria-reducing properties are inherent to the film featuring PURE ZONE® technology (when stored in its original packaging):
and confirmed for Golden staph (Staphylococcus aureus) (Standard ISO 22196) (report Eurofins STUYHA20AA0041-1):
 - Initially: > 99.9 %
 - After 6 years: > 99.9 %

Vertical indoor exposure: up to 5 years (in areas not subject to frequent handling or high visitor frequency).

A film applied in areas of frequent handling (e.g.: handles) or high visitor frequency will be subject to repeated abrasion that will reduce its durability (change of appearance, lifting, etc.). The film durability depends on the intensity and frequency of the mechanical stress to which it is exposed.

CERTIFICATION:

Fire-smoke classification



Fire-smoke classification standard
French standard for fire behaviour

Fire-smoke classification protocol no.
EFR-21-000936



Reach compliance

The PURZON060B and PURZON060M films comply with the Biocidal Products Regulation (BPR) and ECHA's list of SVHC (Substances of very high concern).

The films contain a biocide (silver phosphate glass) that complies with the REACH Directive. This active ingredient is registered in the BPR list under the CAS number: 308069-39-8.

The films do not contain any ingredient described in the SVHC list.

ANTIMICROBIAL activity - PURE ZONE TECHNOLOGY

Antiviral activity on the coronavirus strain SARS-CoV-2 (according to the ISO 21702 standard) (report VirHealth no. R2103FSHEX002):

Up to 97 % after a contact time of 60 min.

Antiviral activity on the Human coronavirus strain HCoV-229E (according to the ISO 21702 standard) (report Fonderephar no. 21-1697):

93.69 % after a contact time of 15 min.,

99.68 % after a contact time of 60 min.

The reduction of > 99.99 % of bacteria (according to ISO 22196) confirmed for the active strains of:

Escherichia coli; (report Eurofins STUYHA21AA0017-1),

Salmonella (Salmonelle enterica); (report Eurofins STUYHA21AA0017-1),

Listeria (Listeria monocytogenes); (report Eurofins STUYHA21AA0017-1),

Methicillin-resistant Staphylococcus aureus (MRSA) (report Eurofins STUYHA21AA0017-1),

Pseudomonas aeruginosa; (report Eurofins STUYHA21AA0017-1).

The reduction of > 99.99 % of bacteria (according to ISO 22196) confirmed for the active strains of:

Golden staph (*Staphylococcus aureus*); (report Eurofins STUYHA21AA0017-1),

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.