



# TECHNICAL DATA SHEET – FLEX – DIGITAL PRINTING UFLEX7PV2



85-µm, adhesive-coated polyurethane film, made from a water-based emulsion, which is free of DMF or similar solvents. Opaque white, thin film, recommended for applications to cotton and polyester textiles (except Softshell). Especially adapted for the creation of letterings, logos or small images. Matt surface finish.

# **FILM FEATURES:**

## Indicative value

Thickness (µm):

85

Good adhesion to cotton and polyester.

For any other type of textile, carry out a test to check the resistance of the fabric to the press temperature and the compatibility of the UFLEX7PV2 film with the cloth.

## **GENERAL PRINTER COMPATIBILITIES:**

	Solvent	Eco-solvent	Latex
UFLEX7PV2	✓	✓	✓

#### LINER:

105-µm polyester liner.

#### **USER'S INSTRUCTIONS:**

- Do not use the UFLEX7PV2 film on Softshell fabrics.
- Print the image in positive mode.
- Cut and weed the image.
  - Minimum cutting size (unprinted areas or perfectly dry, printed areas): 0.6 cm (0.24 in.) (height of letters).
- It is preferable to apply the film to previously washed fabrics.
- Carry out the transfer using the transfer films HEX960 or HEX860.
  - Apply the tape to the UFLEX7PV2 using a squeegee, pressing hard.
- Preheat press and textile prior to application.
- Indicative temperature and pressing duration depend on the fabric:
  - 140 °C (284 °F) for 15 seconds on cotton.
- In any case, always perform a preliminary trial so as to best adjust the pressing conditions before carrying out large series.

- Carefully remove the transfer tape while the film is still hot.
- The final step consists of placing parchment paper on the graphic's surface and pressing the entire assembly for 5 seconds at 140 °C (284 °F).
- After pressing, wait for at least 24 hours before washing the garment.

For better ink durability, it is preferable to wait for one week before carrying out the first washing.

- The maximum washing machine temperature is 60 °C (140 °F). Turn your garment inside out for washing and use laundry products without chlorine bleach.
- Tumble drying is prohibited.
- Iron your garment inside out.

## **OPERATING RECOMMENDATIONS:**

• For each new application of UFLEX7PV2 films to Lycra® based fabrics, verify the compatibility of the UFLEX7PV2 film with this material by producing a garment corresponding to the end product.

Due to the high variability of these substrates, HEXIS decline all responsibility related to the behaviour of the end product.

- The use of softeners is not recommended since it can cause an alteration of the flex film adhesion to the fabric.
- For more information on the application method of UFLEX7PV2, please refer to the Application Guide PRINTFLEX on the "Professionals" pages, category "Films for textile" on our website www.hexis-graphics.com.

## **STORAGE:**

Shelf life (before use):

The shelf life of this film is I year when stored in its unopened original packaging at a temperature ranging from 15  $^{\circ}$ C to 25  $^{\circ}$ C (+59  $^{\circ}$ F to +77  $^{\circ}$ F) with relative humidity between 30  $^{\circ}$ 8 and 70  $^{\circ}$ 8.