



TECHNICAL DATA SHEET - PROTECTIVE FILM

DSMAT2

Film for decoration purposes. Indoor application.

Colour: Matt white etched glass.

FILM FEATURES:

Average values

(values for a film applied to a 3-mm clear glazing)

- Solar energy rejection (heat) (%): 29
- Solar reflection (%): 18
- Solar absorption (%): 19
- Solar transmission (%): 63
- Visible light transmission (%): 69
- Visible light reflection (%): 18
- UV transmission (%): 5

FILM COMPATIBILITY: (vertical application)

Type of glazing		Compatibility
Simple glazing	Clear	Yes
	Tinted	Yes
	Tinted, mirrored	Yes
Double glazing	Clear	Yes
	Tinted	Yes
	Tinted, mirrored	Yes
	Low emission (inert gas fill)	Yes
	Laminated, clear (laminated glass facing outwards of the building)	Yes
	Laminated, clear (laminated glass facing inwards of the building)	Yes

USER'S INSTRUCTIONS:

- During storage, always handle with clean and dry hands.
- Indoor application.
- Application with soapy water only.
- Adhesion to glass, except grained substrates.
- Application to vertical glass surfaces, up to a maximum of 2.5 m².
- Only use special tools dedicated to the application of window films.
- Always remove the liner at the moment right before application, and squeegee the film right after as instructed during the HEXIS training courses.
- If peeled off after its application, the deterioration of the structure and appearance of the film will be irreversible.
- After application you must wait for one month before cleaning the surface with soapy water for the first time.
- The film should not be covered by stickers or self-adhesive films.

RECOMMENDATIONS:

- For further information on the application method of the DSMAT2 film, please refer to the Application Guides available under the "Professionals" headings, category "Solar and safety films" on our website at www.hexis-graphics.com.

STORAGE:

- Shelf life (before application):

The shelf life of this film is 3 years if it is stored at a temperature ranging from 59 °F to 77 °F (from 15 °C to 25 °C), with relative humidity of 50 %, in a horizontal position, in a dust-free environment.

DURABILITY:

- Vertical exposure: 20 years.

WARRANTY:

- HEXIS warrants the DSMAT2 in vertical exposure for 10 years against crackling and yellowing of the film.

NOTES:

The compatibilities indicated in this table are provided for information purposes only and must be confirmed on a case-by-case basis. Due to the great variety of glazing and exposure possibilities, it is the responsibility of the customer/the person in charge of application to carry out a detailed compatibility study between the glass/film and the use-related impacts. These evaluations should be accomplished prior to product implementation in order to determine if it is suitable or not for the intended purpose. All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.