



## TECHNICAL DATA SHEET - DIGITAL PRINTING - PAPER P130

A 148- $\mu$ m paper for solvent, eco-solvent, UV and latex inkjet printing. Satin surface finish.

### **FILM FEATURES:**

	<u>Average values</u>	<u>Standard</u>
• Total thickness ( $\mu$ m):	148	ISO 534
• Total weight of the product ( $\text{g}/\text{m}^2$ ):	130	ISO 536
• Opacity (%):	> 89	ISO 2471

### **GENERAL PRINTER COMPATIBILITIES:**

	<b>Solvent</b>	<b>Eco-solvent</b>	<b>Latex</b>	<b>UV</b>
<b>P130</b>	✓	✓	✓	✓

### **USER'S INSTRUCTIONS:**

- Use the ICC HEXIS profiles available on our website [www.hexis-graphics.com](http://www.hexis-graphics.com) to perform high quality work while optimising the quantity of ink required for this substrate.
- Touch-dry after less than 5 minutes depending on printer used.
- Comply with the conditions of storage temperature and hygometry before printing.
- Water- and weather-resistant paper.

### **OPERATING RECOMMENDATIONS:**

- For any lamination, coating or other, optimal drying time for the inks is 24 hours.
- The surface finish of your printing may be modified/improved/protected by a judicious choice of laminating films V650/V700 Matt, Satin or Glossy.

*It is recommended to laminate the P130 for any long-term outdoor exposure or if it is subject to severe climate conditions.*

- The latex inks are water-sensitive and need to be protected in case of outdoor exposure.
- In the event of frequent cleaning of the graphics, its edges and corners must be protected with a sealing tape or varnish.

### **STORAGE:**

- Shelf life (before application):

The shelf life of this film is 1 year when stored unopened in its original packaging at a temperature ranging from 10 °C to 30 °C (+50 °F to +86 °F) with relative humidity between 30 % and 65 %.

### **NOTES:**

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use. All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website [www.hexis-graphics.com](http://www.hexis-graphics.com).