



# TECHNICAL DATA SHEET - DIGITAL PRINTING - LAMINATE - PERMANENT ADHESIVE **PG3036UVB**

Film composed of a 36-µm, very transparent, UV-treated polyester, which is coated with a pressure-sensitive acrylic adhesive. Intended for the cold lamination or protection of 2D flat surfaces, the film is easy to clean and can be used as anti-graffiti protection. Glossy surface finish.

## **FILM FEATURES:**

|     | ۰ |     | . • |                |     |     |
|-----|---|-----|-----|----------------|-----|-----|
| ınd |   | ~~  | •"  | 110            | 1/2 |     |
| ши  | п | L.A | L.I | v $\leftarrow$ | va  | lue |
|     |   |     |     |                |     |     |

• Thickness (µm): 36

Average values Standard

Tensile strength (N/25 mm): > 100 HEXNFX41021

Shrinkage 168 hours at 70 °C (158 °F) (mm): < 0.2 HEXRET001</li>

## LINER:

- Transparent, 36-µm, silicone-coated PET liner.
- Stable under hygrometric variations.

## **ADHESIVE PROPERTIES:**

(Measured average values at publication of the technical data sheet)

|   |   | Average values | <u>Standard</u> |
|---|---|----------------|-----------------|
| • | Peel strength test 180° on glass (N/25 mm): |                | HEXFTM001       |
|   | after 20 minutes of application             | 14             |                 |
|   | after 24 hours of application               | 18             |                 |
| • | Initial tack (N/25 mm):                     | 18             | HEXFTM009       |
| • | Release (N/25 mm):                          | 0.1            | HEXFTM003       |

Resistance to solvents: the adhesive is resistant to most chemicals (alcohol, diluted acids, oils).

## **ADHESIVE:**

- Solvent-based acrylic adhesive.
- Immediate and permanent adhesion.

#### **USER'S INSTRUCTIONS:**

- Anti-UV and anti-graffiti protection of 2D flat surfaces.
- Dry application only.
- For an outdoor application, an extra margin of 2 cm (0.79 in.) is preferable.
- Recommended minimum application temperature: +10 °C (+50 °F).
- Range of film operating temperatures: from -40  $^{\circ}$ C to +90  $^{\circ}$ C (-40  $^{\circ}$ F to +194  $^{\circ}$ F).
- Only use non-felted squeegees during application.
- The film can be cleaned with a non-abrasive sponge or a soft cloth and acetone, alcohol, soapy water or HEX'AG.
- In the case of an already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

### **OPERATING RECOMMENDATIONS:**

- For any lamination, coating or other of a HEXIS digital printing film, optimal drying time for the inks is:
  - 48 hours for a cast film;
  - 24 hours for a calendered film.
- When using as lamination, make sure that the tensions of each film (film to be laminated and laminate) are the same during the lamination process.
- When repositioning a digital print film complex + PG3036UVB, white lines may appear in the laminating film PG3036UVB during application.

For a line-free result, HEXIS recommend using masking tape to correctly adjust the position of the compound (always with its liner) on the substrate before removing the liner and applying the film.

#### **STORAGE:**

• Shelf life (before application):

The shelf life of this film is 2 years when stored upright in its original packaging in a dust-free environment at a temperature ranging from +15 °C and +25 °C (+59 °F to +77 °F) with relative humidity of 50 %.

## **DURABILITY:** (Central European climate)

 Vertical exposure on flat surface: Outdoors: 5 years.

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the "Conversion rules for indicative durabilities according to geographical area" chart available under Durability, on the "Professionals" pages on our site www.hexis-graphics.com.

#### **NOTES:**

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use. All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.