



AG700

PRODUCT DESCRIPTION:

Film composed of a 36- μ m polyester, which is coated with a pressure-sensitive, acrylic adhesive. Glossy surface finish; intended for cold laminating.

FILM FEATURES:

• Thickness	(Indicative value) 36 μm	
• Tensile strength	(Average values) > 100 N/25 mm	Method HEXNFX41021
• Surface roughness	(Average values) < 5* μm	Method HEXRUG001
• Shrinkage 168 hours at 70 °C (158 °F)	(Average values) < 0.2 mm	Method HEXRET001

* A surface roughness of less than 10 μ m indicates a potentially hazardous floor in wet conditions. Do not apply to floors.

LINER:

- Silicone-coated Kraft paper 87 g/m² with grey HEXIS print.
- Stable under hygrometric variations

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

• Peel strength test at 180°; Measurement support glass	(Average values)	Method
after 20 minutes of application	15 N/25 mm	HEXFMT001
after 24 hours of application	(Average values) 16 N/25 mm	Method HEXFMT001
• Initial tack	(Average values) 16 N/25 mm	Method HEXFMT009
• Release	(Average values) 0.1 N/25 mm	Method HEXFMT003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils, ketones).		

ADHESIVE:

- Solvent-based acrylic adhesive (non-repositionable adhesive).
- Immediate and permanent adhesion; suitable for wet application.

USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +10 °C (+50 °F)
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)
- The film can be cleaned using non-abrasive accessories, with acetone, alcohol, soapy water or HEX'AG.
- In the case of an already painted substrate, apply to undamaged original paintwork only. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.



STORAGE:



Storage period before use
2 years



Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage
with relative humidity of 50 %



Storage area
in a dust-free environment



Storage method before use
in its original packaging



Orientation of rolls before use
vertically

DURABILITY: (Central European climate)

- Vertical outdoor exposure:
Graffiti-free, not cleaned using solvents: 3 years.
Cleaned film: dependent on the method and frequency of the cleaning.

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site www.hexis-graphics.com.

CERTIFICATION:

Fire-smoke classification



Fire-smoke classification standard
NF P 92-507 (fév. 2004)

Fire-smoke classification protocol no.
EFR-24-001130

- The product is 100 % graffiti-resistant in accordance with the NF F 31-112 standard for graffiti protection of railway vehicles.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.