



HEX 900 HIGH TACK

PRODUCT DESCRIPTION:

83-µm paper which is coated with a pressure-sensitive rubber adhesive.

FILM FEATURES:

- Thickness (Indicative value)
83 µm
- Tensile strength (Indicative value)
88 N/25 mm
- Elongation at break (Indicative value)
3 %

ADHESIVE PROPERTIES:

- Measurement support steel (Indicative value)
4 N/25 mm
- Film's adhesion

ADHESIVE:

- Natural rubber-based adhesive.
- Immediate adhesion.

USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +15 °C (+59 °F)
- Operating temperature range: +15 °C to +35 °C (+59 °F to +95 °F)
- For best results, the letter transferring process should preferably be carried out on the same day that the transfer paper has been applied to the letters.

STORAGE:



Storage period before use
1 year



Storage temperature
+21 °C (+70 °F)



Relative humidity during storage
with relative humidity of 50 %



Storage method before use
in its unopened original packaging

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.