



# HEX 915

## PRODUCT DESCRIPTION:

A 110-µm, embossed PP film, which is coated with a pressure-sensitive, acrylic adhesive.

## FILM FEATURES:

- Thickness (Indicative value)  
**110 µm**

## ADHESIVE PROPERTIES:

- Film's adhesion (Indicative value)  
**1,1 N/cm**

## ADHESIVE:

- Acrylic adhesive.
- Permanent adhesion, optimal after 48 hours of contact and complete after 7 days.

## USER'S INSTRUCTIONS:

- Dry application method
- Recommended minimum application temperature: +10 °C (+50 °F)
- Operating temperature range: +15 °C to +35 °C (+59 °F to +95 °F)
- May be used for transferring glossy and matt films.
- Ideal for transferring letterings of between 5 cm and 31 cm.
- For best results, the letter transferring process should preferably be carried out on the same day that the transfer film has been applied to the letters.

## STORAGE:

- Storage period before use  
**6 months**
- Storage temperature  
**+15 °C to +25 °C (+59 °F to +77 °F)**

- Relative humidity during storage  
**with relative humidity between 30 % and 70 %**
- Storage method before use  
**in its unopened original packaging**

## NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website [www.hexis-graphics.com](http://www.hexis-graphics.com).