



SPM

PRODUCT DESCRIPTION:

The SURFACE PROTECTION SPM film is an adhesive film developed for protecting all substrates that do not require major aesthetic criteria. Its excellent shock-absorbing properties protect your substrate against physical, mechanical, chemical and solar stress. Matt surface finish.

FILM FEATURES:

• Thickness	(Indicative value) 150 µm	
• Tensile strength	(Average values) > 100 N/25 mm	Method HEXNFX41021
• Elongation at break	(Average values) > 350 %	Method HEXNFX41021
• Shrinkage 168 hours at 70 °C (158 °F)	(Average values) < 0.2 mm	Method HEXRET001

LINER:

- Silicone-coated PET liner.

ADHESIVE PROPERTIES:

• Peel strength test at 180°		
after 20 minutes of application	(Average values) 22 N /25 mm	Method HEXFTM001
after 24 hours of application	(Average values) 23 N/25 mm	Method HEXFTM001
• Initial tack	(Average values) 13 N/25 mm	Method HEXFTM009
• Release	(Average values) 0.1 N/25 mm	Method HEXFTM003

ADHESIVE:

- Solvent-based acrylic adhesive.
- Immediate and permanent adhesion, optimal after 24 hours of contact.

USER'S INSTRUCTIONS:

- Wet application method
- Recommended minimum application temperature: +10 °C (+50 °F) Apply preferably between +15 °C and +35 °C (+59 °F and +95 °F).
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)

- The SPM film is intended for surface protection. Its matt surface finish may be altered by matt stripes (mottling) and/or surface imperfections. Therefore its use should be reserved for applications not requiring an aesthetic aspect.
- Cut the film to the size of the part to be wrapped, allowing +10 cm (4 in.) of extra margin.

The remaining film must be stored on its original core (do not cut the rolls into several lengths or widths, do not repackage the product); the roll must be closed immediately and properly (masking tape or roll-collars) after use in order to preserve all its qualities.

- Wet application directly to the surface that is to be protected; check the compatibility of the substrate with water.
- Apply to a surface that is clean and free from any traces of contaminants (dust, grease, wax, silicone, etc.).

Particular care must be taken to clean the angles and periphery of the target surfaces in order to enable the film to adhere properly to the surface.

- In the case of an already painted substrate, apply to undamaged original paintwork only. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.



OPERATING RECOMMENDATIONS:

- Conformable product developed for protecting all substrates.
- Excellent protection against vandalism.
- The improved surface sliding of the SPM film enables you to reduce squeegee friction during application and facilitates the film cleaning.
- To facilitate application, HEXIS have several types of squeegees in their range of accessories, ranging from softer to harder (plastic or felt).

STORAGE:



Storage period before use
1 year



Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage
with relative humidity of 50 %



Storage area
in a dust-free environment



Storage method before use
in its unopened original packaging



Orientation of rolls before use
vertically

DURABILITY: (climat Europe centrale)

- Vertical exposure:
up to 7 years (under normal road use conditions).
- Lifespan depends on the type of substrate, substrate preparation, exposure conditions and nature and frequency of the cleaning.

For instance, it is estimated that a south-facing exposure (in the northern hemisphere) will divide the durability by two. The same applies to a horizontal exposure. In addition, elevated temperatures (above +50 °C) (+122 °F) or pollution significantly reduce this durability.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.