

## V203EG



### PRODUCT DESCRIPTION:

Printable film composed of an 80- $\mu$ m, calendered, polymeric PVC, which is coated with a pressure-sensitive acrylic adhesive. For solvent, eco-solvent, latex and UV inkjet printing. Etched glass surface finish.

### FILM FEATURES:

• Thickness	(Indicative value) <b>80 <math>\mu</math>m</b>	
• Total thickness	(Indicative value) <b>225 <math>\mu</math>m</b>	
• Total weight	(Average values) <b>260 g/m<sup>2</sup></b>	Method <b>HEXGSM001</b>
• Tensile strength	(Average values) <b>min. 35 N/25 mm</b>	Method <b>HEXNFX41021</b>
• Elongation at break	(Average values) <b>min. 100 %</b>	Method <b>HEXNFX41021</b>
• Shrinkage 168 hours at 70 °C (158 °F)	(Average values) <b>&lt; 0.4 mm</b>	Method <b>HEXRET001</b>

### LINER:

- Silicone-coated Kraft paper 137 g/m<sup>2</sup> with light grey HEXIS print.
- Stable under hygrometric variations

### ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

• Peel strength test at 180°; Measurement support glass		
after 20 minutes of application	(Average values) <b>18 N/25 mm</b>	Method <b>HEXFTM001</b>
after 24 hours of application	(Average values) <b>23 N/25 mm</b>	Method <b>HEXFTM001</b>
• Initial tack	(Average values) <b>19 N/25 mm</b>	Method <b>HEXFTM009</b>
• Release	(Average values) <b>0.2 N/25 mm</b>	Method <b>HEXFTM003</b>
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

### ADHESIVE:


- Solvent-based acrylic adhesive.
- Adhesion is immediate and permanent (non-repositionable adhesive), suitable for wet application.

### PRINTING GUIDE:

- Touch-dry after less than 15 minutes depending on printer used.
- Optimal drying time for the inks before laminating, coating or further processing is 24 hours.

### USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +10 °C (+50 °F)
- Operating temperature range: -40 °C to +90 °C (-40 °F to +194 °F)
- Adhesion to glass, steel, aluminium, PVC, melamine, etc. except grain substrates or substrates coated with acrylic paint.
- In the case of an already painted substrate, apply to undamaged original paintwork only. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.



## OPERATING RECOMMENDATIONS:

**Caution:** Applying a laminate can strongly reduce the etched glass surface finish of the V203EG film.

## STORAGE:



Storage period before use  
**1 year**



Storage temperature  
**+15 °C to +25 °C (+59 °F to +77 °F)**



Relative humidity during storage  
**with relative humidity of 50 %**



Storage area  
**in a dust-free environment**



Storage method before use  
**in its original packaging**



Orientation of rolls before use  
**vertically**

## DURABILITY: (Central European climate)

- Vertical outdoor exposure:  
Unprinted: 5 years.  
Printed and laminated:  
- PC500: 5 years,  
- V750: 4 years,  
- VCR750: 3 years.  
Printed: 2 years.

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site [www.hexis-graphics.com](http://www.hexis-graphics.com).

## NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website [www.hexis-graphics.com](http://www.hexis-graphics.com).