



VCR650B

PRODUCT DESCRIPTION:

Film composed of a 70- μ m calendered, monomeric PVC, which is coated with a pressure-sensitive acrylic adhesive. Glossy surface finish for cold laminating; mainly for mechanical protection purposes. Particularly suitable for laminating UV inkjet printing.

FILM FEATURES:

• Thickness	(Indicative value) 70 μm	
• Tensile strength	(Average values) min. 30 N/25 mm	Method HEXNFX41021
• Elongation at break	(Average values) min. 80 %	Method HEXNFX41021
• Shrinkage 168 hours at 70 °C (158 °F)	(Average values) < 1.2 mm	Method HEXRET001

LINER:

- Silicone-coated Kraft paper 87 g/m² with grey HEXIS print.
- Stable under hygrometric variations

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

• Peel strength test at 180°; Measurement support glass		
after 20 minutes of application	(Average values) 19 N/25 mm	Method HEXFTM001
after 24 hours of application	(Average values) 22 N/25 mm	Method HEXFTM001
• Initial tack	(Average values) 22 N/25 mm	Method HEXFTM009
• Release	(Average values) 0.1 N/25 mm	Method HEXFTM003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

ADHESIVE:

- Solvent-based acrylic adhesive.
- Immediate and permanent adhesion.

USER'S INSTRUCTIONS:

- Recommended minimum application temperature: +10 °C to +35 °C (+50 °F to +95 °F)
- Operating temperature range: -30 °C to +60 °C (-22 °F to +140 °F)
- Particularly suitable for cold laminating UV inkjet prints.

Although the ink is solid immediately after printing, the polymerisation and reticulation time of the inks is 24 hours (variable depending upon the printer used and the quantity of ink applied). Please comply with this minimum waiting time before laminating the UV inkjet-printed film.

- Resistance against mechanical stress.
- Using this protective film also enables you to modify the products's visual aspect by providing it with a gloss surface finish.
- Depending on the type of surface to be protected: when applied to paintworks or «non dry» inkjet prints, the VCR650B laminate may show signs of shrinkage. To avoid such alterations or for medium-term applications, we strongly recommend the use of our VCR750 laminate.
- In the case of an already painted substrate, apply to undamaged original paintwork only. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.



STORAGE:



Storage period before use
1 year



Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F)



Relative humidity during storage
with relative humidity of 50 %



Storage area
in a dust-free environment



Storage method before use
in its original packaging



Orientation of rolls before use
vertically

DURABILITY: (Central European climate)

- Up to 1.5 years only for the laminate but not for the graphics.

The durability of the laminated print depends on the printing technology used and the inks used. Consult the ink manufacturer.

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the «Conversion rules for indicative durabilities according to geographical area» chart available under Durability, on the «Professionals» pages on our site www.hexis-graphics.com.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods which are available on request. Please feel free to contact us to get the latest instructions in use. All the published information is based on measurements regularly performed in the laboratory. It does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.