



# TECHNICAL DATA SHEET - DIGITAL PRINTING – POLYPROPYLENE - OPAQUE **POP200ECOS**

205-µm, white/grey, opaque polypropylene film. For solvent, eco-solvent, latex and UV inkjet printing. Satin surface finish.

# **FILM FEATURES:**

#### Indicative values

Total thickness of the product (µm): 205
 Total weight of the product (g/m²): 170

# **GENERAL PRINTER COMPATIBILITIES:**

	Solvent	Eco-solvent	Latex	UY
POP200ECOS	✓	✓	✓	✓

## **USER'S INSTRUCTIONS:**

• Printing temperature range: +15 °C to +30 °C (+59 °F to +86 °F) with 30-60 % humidity.

For latex printing, always carry out a preliminary test to define optimal adjustment of printing parameters and ink drying temperatures in order to avoid any risk of material deformation.

- Touch-dry after less than 10 minutes depending on printer used.
- Suitable for roll-up and wall displays.

Anti-curling film: prevents self-curling. Scratch-resistant film: protective lamination not necessary.

The surface finish of your printing may be modified/improved by the judicious choice of one
of the laminating films V650, V700, V750 or GFLI130. DO NOT USE heat-sealing (heat
encapsulating) film.

During lamination, make sure that the tension between the protection film and the visual is the same in order to avoid any unwanted curling effect.

For any lamination, coating or other, optimal drying time for the inks is 24 hours.

## **STORAGE:**

Shelf life (before application):

The shelf life of this film is I year when stored unopened in its original packaging at a temperature ranging from  $+10\,^{\circ}\text{C}$  to  $+30\,^{\circ}\text{C}$  ( $+50\,^{\circ}\text{F}$  to  $+86\,^{\circ}\text{F}$ ) with relative humidity between 35 % and 65 %.

#### NOTES: